



RAW COLLECTION
Grigio Elegante | Double Wave Design

Grigio Elegante | *Marble*

Test	Std.	Unit	Ave. Value	Condition
Dry Density	EN 1936	(gr/cm3)	2.71	-
Saturated Density	EN 1936	(gr/cm3)	2.72	-
Porosity	EN 1936	(%)	0.22	-
Specific Gravity	EN 1936	(Kg/m3)	2.72	-
Water Absorption Under Atmosphere Pressure	EN 13755	(%)	0.08	-
Capillary Water Absorption	EN 1925	(Kg/m2)	0.26	-
Compressive Strength	EN 1926	(MPa)	54.35	Dry
Tensile Strength	ISRM 1981	(MPa)	4.04	Dry
Flexural Strength	EN 12372	(MPa)	7.02	Dry
Resistance to Salt Crystallization	EN 12370	(Mass loss %)	-9.63	After 48 Cycles
Resistance to Freeze-Thaw	EN 12371	(Mass loss %)	-0.02	After 48 Cycles
Resistance to Acid (H2SO4)	EN 13919	(Mass loss %)	-0.43	After 48 Cycles
Thermal Shock	EN 14066	(Mass loss %)	-0.03	After 48 Cycles

Details


Formats Available | Slabs

Thickness Available | 2cm, 3cm


Available Designs | Cotton, Double Wave, Hydro, Lineal, Lineal Plus, Microdot, Rock

Applications | Interior and Exterior Wall Cladding

Designs




Cotton Design



Double Wave Design



Lineal Design



Lineal Plus Design