




Sanded White | *Granite*

Test	Std.	Unit	Ave. Value	Condition
Dry Density	EN 1936	(gr/cm3)	2.64	-
Saturated Density	EN 1936	(gr/cm3)	2.65	-
Porosity	EN 1936	(%)	1.19	-
Water Absorption Under Atmosphere Pressure	EN 13755	(%)	0.55	-
Capillary Water Absorption	EN 1925	(Kg/m2)	1.2	-
Flexural Strength	EN 12372	(MPa)	12.05	Dry
Resistance to Salt Crystallization	EN 12370	(Mass loss %)	-0.26	After 48 Cycles
Resistance to Freeze-Thaw	EN 12371	(Mass loss %)	0	After 48 Cycles
Resistance to Acid (H2SO4)	EN 13919	(Mass loss %)	0	After 48 Cycles

Details

- Formats Available | Slabs
- Thickness Available | 1cm, 2cm, 3cm
- Available Designs | Lineal Extreme Light, Lineal Plus, Oblique
- Applications | Interior and Exterior Wall Cladding

Designs



Lineal Plus Design



Oblique Design