



RAW COLLECTION
Volga Blue | Microdot Design

Volga Blue | Granite

Test	Std.	Unit	Ave. Value	Condition
Dry Density	EN 1936	(gr/cm3)	2.72	-
Saturated Density	EN 1936	(gr/cm3)	2.73	-
Porosity	EN 1936	(%)	0.52	-
Specific Gravity	EN 1936	(Kg/m3)	2.74	-
Water Absorption Under Atmosphere Pressure	EN 13755	(%)	0.19	-
Thermal Expansion Coefficient	EN 14581	10 ⁻⁶ C ⁻¹	7.3	-
Capillary Water Absorption	EN 1925	(Kg/m2)	0.39	-
Compressive Strength	EN 1926	(MPa)	122.88	Dry
Tensile Strength	ISRM 1981	(MPa)	7.1	Dry
Flexural Strength	EN 12372	(MPa)	18.33	Dry
Resistance to Salt Crystallization	EN 12370	(Mass loss %)	-0.11	After 48 Cycles
Resistance to Freeze-Thaw	EN 12371	(Mass loss %)	-0.03	After 48 Cycles
Resistance to Acid (H2SO4)	EN 13919	(Mass loss %)	-0.02	After 48 Cycles
Thermal Shock	EN 14066	(Mass loss %)	-0.02	After 48 Cycles

Details


Formats Available | Slabs

Thickness Available | 2cm, 3cm


Available Designs | Casual, Cotton, Double Wave, Lava, Lineal, Lineal Extreme Dark, Lineal Extreme Light, Lineal Plus, Lineal Plus Dark, Microdot, Rock, Super Rock, Velvet

Applications | Interior and Exterior Wall Cladding


Designs




Casual Design




Cotton Design




Lineal Design




Lineal Plus Design




Double Wave Design




Rock Design




Super Rock Design



Lava Design



Velvet Design



Microdot Design